Case: 1:22-cv-02937 Document #: 1-1 Filed: 06/06/22 Page 1 of 3 PageID #:16

EXHIBIT A

Case: 1:22-cv-02937 Document #: 1-1 Filed: 06/06/22 Page 2 of 3 PageID #:17



DLA Approved Independent Testing Laboratory

4207-1 Milgen Road, Columbus, GA 31907 Telephone: 844-309-6337 www.textest.com

TexTesT Report: 13163
Date: 4/15/2022
Page: 1 of 2

CLIENT: SHEEHAN & ASSOCIATES, P.C.

60 Cuttermill Road Great Neck, NY 11021

ATTN: Spencer Sheehan

SAMPLE IDENTIFICATION: SAMPLE #1 SEALY PREMIUM COMFORT 1250 Thread Count

KING SHEET SUPERIOR MOISTURE WICKING

FABRIC: 48% POLYESTER/44% COTTON/8% MODAL Made in India

RN 17119 0 2241534251 3

END & PICK COUNT ASTM D 3775

Warp 57 Filling 166

Total Thread Count 223

A deceptive count of each filament of each warp yarn each filament yarn has 19 filaments

57x19 = 1083

+ 166

Total Count 1249

TEXTEST

Ann R. Underwood

signed by

13163 2 of 2



